

TECHNICAL DATA

2763

PVC Adhesive Tape

DESCRIPTION

Scapa 2763 is a plasticized PVC tape, single coated with a rubber adhesive. **Scapa 2763** is available in black and yellow.

APPLICATIONS

- Wrapping of automotive electrical wiring harnesses
- Hand application
- Product designed for applications which require a good temperature resistance, class T2 (105°C)

PRODUCT BENEFITS

- Tough, flexible and conformable
- Easy and smooth unwind
- Self-extinguishing on harness
- Lead free
- Conforms to European Directive 2000/53/EC for End of Vehicle Life (ELV) recycling (does not contain heavy metals)
- Operating temperature between -30°C to +105°C

Issue: 8

Date: 27/02/2009

Page 1 of 2

2763.doc

www.scapa.com

The information supplied is accurate to the best of Scape's knowledge and is based upon all current data available to it. Properties quoted are typical and do not interefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our behnical advice to be regarded as an expression of opinion only and ellihough such advice to given in good faith, it shall not, in any circumstances, be regarded as the session of opinion only and ellihough such advice to given in good faith, it shall not, in any circumstances, be regarded as the session of opinion only and ellihough such advice to given in good faith, it shall not, in any circumstances, be regarded as the session of opinion on y and ellihough such advice to given in good in respect of our products will be strictly limited to the value of those also entry and shall not extended to any consequential loss whatsoever and howscoever arising. Freedom from Patent Rights must not be assumed. This decument does not identify limited to the accuracy with a customer and shall not extended to any consequential loss whatsoever and howscoever arising. Freedom from Patent Rights must not be assumed. This decument does not identify limited to the accuracy with a customer and shall not extended to any consequential loss.

TECHNICAL PROPERTIES

	Unit	Nominal Value	Test Method
Thickness	mm	0.11	AFERA 5006
Tensile Strength	N/cm	25	AFERA 5004
Elongation at Break	%	180	AFERA 5004
Peel Adhesion to Steel	N/cm	1.5	AFERA 5001
Peel Adhesion to Backing	N/cm	1.5	AFERA 5001
Flame Resistance	1	Self-extinguishing	RENAULT/PSA
	/	Туре В	

STANDARD PRESENTATION

- Roll length: 33metres
 - Roll width: 9. 12. 19. 25 and 30mm
- Core:

- 38mm Scapa branded cardboard core Cardboard - Towerpack Packaging:
- Black and yellow Colours:

RECOMMENDATIONS

Rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. The storage temperature should be between +5°C and +25°C. A strict use-by date of 24 months from the date of manufacture is recommended.

The tape should be applied with sufficient tension and a minimum of two layers with a half overlap to ensure optimum bonding. The final layer should be wrapped with a lower tension to prevent flagging effects.

Surfaces should be clean, dry and free of dust, grease, oil or other contaminants.

Issue: 8

Date: 27/02/2009

Page 2 of 2

2763 doc

www.scapa.com

The information supplied is accurate to the best of Seara's knowledge and is based upon all current data available to it. Properties quoted are typical and do not interefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such advice is given in good faith, it shall not, in any cincumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of these products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever and how some arising. Freedom from Patient Rights must not be assumed. This document does not form part of any contract with a customer